

## 600T200-18 Track



Product Line: 600EDT200-18- The Edge™ Performance 20 (18 mil)

Coating: G40 (standard), G60 (special order)

Specification Section: 09.22.16 (Non-Structural Metal Framing)

GEOMETRIC PROPERTIES			
Web Depth	6 in.	Yield Strength, Fy	55 ksi
Leg Width	2 in.	Design Thickness	0.0188 in.
		Min. Steel Thickness	0.0179 in.

GROSS PROPERTIES		
Area (in <sup>2</sup> )	Total cross-sectional steel area	0.1889
Weight (lb/ft)	Linear weight per foot	0.642
I <sub>x</sub> (in <sup>4</sup> )	Moment of inertia about the x-axis	1.0453
S <sub>x</sub> (in <sup>3</sup> )	Section modulus about the x-axis	0.3417
R <sub>x</sub> (in)	Radius of gyration about the x-axis	2.353
I <sub>y</sub> (in <sup>4</sup> )	Moment of inertia about the y-axis	0.0695
R <sub>y</sub> (in)	Radius of gyration about the y-axis	0.6065
EFFECTIVE PROPERTIES		
Area (in <sup>2</sup> )	Effective area	0.0315
I <sub>xe</sub> (in <sup>3</sup> )	Effective moment of inertia (x-axis)	0.4175
S <sub>xe</sub> (in <sup>3</sup> )	Effective section modulus (x-axis)	0.0902
Ma (in-k)	Allowable moment capacity	1.8042
V <sub>y</sub> (lb)	Allowable shear force in web	79
TORSIONAL PROPERTIES		
J x 1000 (in <sup>4</sup> )	St. Venant torsional constant	0.0222
C <sub>w</sub> (in <sup>6</sup> )	Warping constant	0.4601
X <sub>o</sub> (in)	Distance from shear center to centroid	1.0571
R <sub>o</sub> (in)	Polar radius of gyration	2.6496
Beta	Torsional Flexural Constant	0.8408



### CODES AND STANDARDS:

Super Stud products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006 – 2024
- Complies with AISI S100-16 (2020) w/S2-20. Effective properties incorporate the strength increase from the cold work of forming
- Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized coating: ASTM A653/A653M or equivalent
- UL Designs: U419, V438, V489, V498, W433, W440
- Tested in accordance with ASTM E119; ANSI/UL 263
- Members and tolerances: ASTM C645; AISI S220, AISI S201, AISI S202
- Meets ASTM C754 when installed properly in structure

For LEED Letter requests please submit through: [www.buysuperstud.com](http://www.buysuperstud.com)