

Super Stud Building Products - Product Submittal

Technical Services: technical@buysuperstud.com

800-477-7883 buysuperstud.com

New Jersey 2960 Woodbridge Avenue Edison, NJ 08837 732-662-6200 **Mississippi** 53 W L Runnels Industrial Dr Hattiesburg, MS 39401 601-584-7550

Specification Section: 05.40.00 (Cold-Formed Metal Framing)

1200S250-118 (50ksi) Standard Punch

118mil (10 ga) Coating: G60 (standard), G90 (special order)

Geometric Properties

Web Depth	12 in	Yield Strength, F _y	50 ksi
Flange Width	2 in	Ultimate, F _u	65 ksi
Lip Length	0.625 in	Punchout Width	1.5 in
Design Thickness	0.1242 in	Punchout Length	4.0 in
Min. Steel Thicknes	s 0.1180 in	-	

Gross Section Properties

Cross Sectional Area (A)	2.0278 in ²
Product Weight per Linear Foot	6.8945 lb/ft
Moment of Inertia (I _x)	36.3563 in ⁴
Section Modulus (S _x)	6.0594 in ³
Radius of Gyration (r _x)	4.2343 in
Weak Axis Moment of Inertia (I _y)	0.7365 in ⁴
Weak Axis Radius of Gyration (r _y)	0.6027 in
Depth-to-Thickness Ratio (h/t)	92

Effective Section Properties, Strong Axis

Effective Area (A _e)	1.0425 in ²
Moment of Inertia for Deflection (I _{xe})	35.7407 in ⁴
Section Modulus (S _{xe})	5.8479 in ³
Allowable Bending Moment (M _a)	175.0879 in-k
Allowable Shear Force in Web (at Punchout) (V _y)	11,034 lb

Torsional Properties

St. Venant Torsion Constant (J x 1000)	10.4266 in ⁴
Warping Constant (C _w)	20.3797 in ⁶
Distance from Shear Center to Neutral Axis (X _o)	0.9468 in
Radius of Gyration (r _o)	4.3805 in
Torsional Flexural Constant (Beta)	0.9533

Codes and Standards

Super Stud products comply with the applicable provisions of the following: International Building Code (IBC): 2006 – 2024

Complies with AISI S100-16 (2020) w/S2-20. Effective properties incorporate the strength increase from the cold work of forming

Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M


Galvanized coating: ASTM A653/A653M

Nonstructural: Members and tolerances: ASTM C645; AISI S220, AISI S201, AISI S202

Meets ASTM C754 when installed properly in structure.

Structural: Members and tolerances: ASTM C955; AISI S240, AISI S201, AISI S202 Meets ASTM C1007 when installed properly in structure.

3rd party Certification



Structural Punchout

First punchout is centered 12" from beginning of member; subsequent punchouts are 24" on center (o.c.). Center of last punchout is no less than 12" from end of member.

Custom stiffened punchouts are available at tighter spacing to reduce thermal transmittance and increase accessibility. Contact Technical Services for additional punchout information.

