

# PROJECT SUBMITTAL SHEET

FOR MORE INFORMATION OR QUESTIONS,  
PLEASE CONTACT THE TECHNICAL DEPARTMENT:  
EB METAL US: (855) 932-6382 | INFO@EBMETAL.US  
SUPER STUD: TECHNICAL@BUYSUPERSTUD.COM

## 362S125-18 (Standard Punch)

**Product Line:** 362NS125-18 NitroStud 18 mil (25 ga.)

**Coating:** G40 (standard), G60 (special order)


**Specification Section:** 09.22.16 (Non-Structural Metal Framing)

| GEOMETRIC PROPERTIES |           |                                |            |
|----------------------|-----------|--------------------------------|------------|
| Web Depth            | 3.625 in. | Yield Strength, F <sub>y</sub> | 33 ksi     |
| Flange Width         | 1.25 in.  | Design Thickness               | 0.0186 in. |
| Lip Length           | .25 in.   | Min. Design Thickness          | 0.0179 in. |

| GROSS PROPERTIES                  |                                     |        |
|-----------------------------------|-------------------------------------|--------|
| Area (in <sup>2</sup> )           | Total cross-sectional steel area    | 0.121  |
| Weight (lb/ft)                    | Linear weight per foot              | 0.41   |
| I <sub>x</sub> (in <sup>4</sup> ) | Moment of inertia about the x-axis  | 0.2433 |
| S <sub>x</sub> (in <sup>3</sup> ) | Section modulus about the x-axis    | 0.1347 |
| R <sub>x</sub> (in)               | Radius of gyration about the x-axis | 1.4156 |
| I <sub>y</sub> (in <sup>4</sup> ) | Moment of inertia about the y-axis  | 0.0208 |
| R <sub>y</sub> (in)               | Radius of gyration about the y-axis | 0.414  |

| EFFECTIVE PROPERTIES               |                                      |        |
|------------------------------------|--------------------------------------|--------|
| I <sub>xe</sub> (in <sup>3</sup> ) | Effective moment of inertia (x-axis) | 0.2004 |
| S <sub>xe</sub> (in <sup>3</sup> ) | Effective section modulus (x-axis)   | 0.0965 |
| M <sub>a</sub> (in-k)              | Allowable moment capacity            | 1.593  |
| M <sub>ad</sub> (in-k)             | Design moment capacity               | 1.593  |
| V <sub>ag</sub> (lb)               | Allowable web crippling              | 258    |
| V <sub>anet</sub> (lb)             | Net allowable shear                  | 211    |

| TORSIONAL PROPERTIES              |                                        |         |
|-----------------------------------|----------------------------------------|---------|
| J x 1000 (in <sup>4</sup> )       | St. Venant torsional constant          | 0.014   |
| C <sub>w</sub> (in <sup>6</sup> ) | Warping constant                       | 0.0555  |
| X <sub>o</sub> (in)               | Distance from shear center to centroid | -0.7346 |
| m (in)                            | Torsional radius of gyration           | 0.3824  |
| R <sub>o</sub> (in)               | Polar radius of gyration               | 1.6477  |
| Beta                              | Torsional Flexural Constant            | 0.8012  |



### CODES AND STANDARDS:

**EB Metal US/Super Stud** products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006 – 2024
- AISI S100-16 (2020) w/S2-20 and AISI S220-20
- Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized coating: ASTM A653/A653M or equivalent
- UL Designs: U411, U412, U419, U420, U425, U435, U451, U465, UL 263, CIKV.R38201, CIKV7.R38201
- Tested in accordance with ASTM E119; ANSI/UL 263
- Members and tolerances: ASTM C645; AISI S220, AISI S201, AISI S202
- Meets ASTM C754 when installed properly in structure.

**For LEED Letter requests please submit through:** [ebmetal.us](http://ebmetal.us). or [buysuperstud.com](http://buysuperstud.com)

**NEW HAMPSHIRE FACILITY**  
12 TALLWOOD DRIVE  
BOW, NH 03304  
P: 601-584-7550

**MISSISSIPPI FACILITY**  
53 W L RUNNELS IND DR  
HATTIESBURG, MS 39401  
P: 601-584-7550

**NEW JERSEY FACILITY**  
2960 WOODBRIDGE AVE  
EDISON, NJ 08837  
P: 732-662-6200