

# PROJECT SUBMITTAL SHEET

FOR MORE INFORMATION OR QUESTIONS,  
PLEASE CONTACT THE TECHNICAL DEPARTMENT:  
SUPER STUD: TECHNICAL@BUYSUPERSTUD.COM

## 362T200-18 (Standard Punch)

**Product Line:** 362EDT200-18 - The Edge™ Performance 20

**Coating:** G40 (standard), G60 (special order)



**Specification Section:** 09.22.16 (Non-Structural Metal Framing)

| GEOMETRIC PROPERTIES |           |                       |            |
|----------------------|-----------|-----------------------|------------|
| Web Depth            | 3.625 in. | Design Thickness      | 0.0188 in. |
| Flange Width         | 2 in.     | Min. Design Thickness | 0.0179 in. |
| Yield Strength, Fy   | 55 ksi    |                       |            |

| GROSS PROPERTIES                  |                                     |        |
|-----------------------------------|-------------------------------------|--------|
| Area (in <sup>2</sup> )           | Total cross-sectional steel area    | 0.1442 |
| Weight (lb/ft)                    | Linear weight per foot              | 0.490  |
| I <sub>x</sub> (in <sup>4</sup> ) | Moment of inertia about the x-axis  | 0.3381 |
| S <sub>x</sub> (in <sup>3</sup> ) | Section modulus about the x-axis    | 0.1807 |
| R <sub>x</sub> (in)               | Radius of gyration about the x-axis | 1.531  |
| I <sub>y</sub> (in <sup>4</sup> ) | Moment of inertia about the y-axis  | 0.0604 |
| R <sub>y</sub> (in)               | Radius of gyration about the y-axis | 0.6471 |
| h/t                               | Depth-to-thickness ratio            | 188    |

| EFFECTIVE PROPERTIES               |                                      |        |
|------------------------------------|--------------------------------------|--------|
| Area (in <sup>2</sup> )            | Effective area                       | 0.0311 |
| I <sub>xe</sub> (in <sup>3</sup> ) | Effective moment of inertia (x-axis) | 0.1485 |
| S <sub>xe</sub> (in <sup>3</sup> ) | Effective section modulus (x-axis)   | 0.0539 |
| Ma (in-k)                          | Allowable moment capacity            | 1.0779 |
| V <sub>y</sub> (lb)                | Allowable shear force in web         | 162    |

| TORSIONAL PROPERTIES              |                                        |        |
|-----------------------------------|----------------------------------------|--------|
| J x 1000 (in <sup>4</sup> )       | St. Venant torsional constant          | 0.0170 |
| C <sub>w</sub> (in <sup>6</sup> ) | Warping constant                       | 0.1454 |
| X <sub>o</sub> (in)               | Distance from shear center to centroid | 1.2802 |
| R <sub>o</sub> (in)               | Polar radius of gyration               | 2.0982 |
| Beta                              | Torsional Flexural Constant            | 0.6277 |



### CODES AND STANDARDS:

*Super Stud/EB Metal US products comply with the applicable provisions of the following:*

- International Building Code (IBC): 2006 – 2024
- Complies with AISI S100-16 (2020) w/S2-20. Effective properties incorporate the strength increase from the cold work of forming
- Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized coating: ASTM A653/A653M or equivalent
- UL Designs: U419, V438, V489, V498, W433, W440
- Tested in accordance with ASTM E119; ANSI/UL 263
- Members and tolerances: ASTM C645; AISI S220, AISI S201, AISI S202
- Meets ASTM C754 when installed properly in structure

*For LEED Letter requests please submit through:* [ebmetal.us](http://ebmetal.us). or [buysuperstud.com](http://buysuperstud.com)

**NEW HAMPSHIRE FACILITY**  
12 TALLWOOD DRIVE  
BOW, NH 03304  
P: 601-584-7550

**MISSISSIPPI FACILITY**  
53 W L RUNNELS IND DR  
HATTIESBURG, MS 39401  
P: 601-584-7550

**NEW JERSEY FACILITY**  
2960 WOODBRIDGE AVE  
EDISON, NJ 08837  
P: 732-662-6200