



# PROJECT SUBMITTAL SHEET

FOR MORE INFORMATION OR QUESTIONS,  
PLEASE CONTACT THE TECHNICAL DEPARTMENT:  
EB METAL US: (855) 932-6382 | INFO@EBMETAL.US  
SUPER STUD: TECHNICAL@BUYSUPERSTUD.COM



## 600T125-33

**Product Line:** 600NT125-33 NitroTrack 33 mil (Structural 20 ga.)

**Coating:** G60 (standard), G90 (special order)


**Specification Section:** 05.40.00 (Cold-Formed Metal Framing)

| GEOMETRIC PROPERTIES |          |                       |            |
|----------------------|----------|-----------------------|------------|
| Web Depth            | 6 in.    | Yield Strength, Fy    | 33 ksi     |
| Leg Width            | 1.25 in. | Design Thickness      | 0.0346 in. |
|                      |          | Min. Design Thickness | 0.0329 in. |

| GROSS PROPERTIES                  |                                     |        |
|-----------------------------------|-------------------------------------|--------|
| Area (in <sup>2</sup> )           | Total cross-sectional steel area    | 0.295  |
| Weight (lb/ft)                    | Linear weight per foot              | 1      |
| I <sub>x</sub> (in <sup>4</sup> ) | Moment of inertia about the x-axis  | 1.4385 |
| S <sub>x</sub> (in <sup>3</sup> ) | Section modulus about the x-axis    | 0.4681 |
| R <sub>x</sub> (in)               | Radius of gyration about the x-axis | 2.2081 |
| I <sub>y</sub> (in <sup>4</sup> ) | Moment of inertia about the y-axis  | 0.0339 |
| R <sub>y</sub> (in)               | Radius of gyration about the y-axis | 0.3387 |

| EFFECTIVE PROPERTIES              |                                      |        |
|-----------------------------------|--------------------------------------|--------|
| I <sub>x</sub> (in <sup>4</sup> ) | Effective moment of inertia (x-axis) | 1.0639 |
| S <sub>x</sub> (in <sup>3</sup> ) | Effective section modulus (x-axis)   | 0.2897 |
| Ma (in-k)                         | Allowable moment capacity            | 5.724  |
| V <sub>a</sub> (lb)               | Allowable web crippling              | 615    |

| TORSIONAL PROPERTIES              |                                        |         |
|-----------------------------------|----------------------------------------|---------|
| J x 1000 (in <sup>4</sup> )       | St. Venant torsional constant          | 0.1177  |
| C <sub>w</sub> (in <sup>6</sup> ) | Warping constant                       | 0.2356  |
| X <sub>o</sub> (in)               | Distance from shear center to centroid | -0.5193 |
| m (in)                            | Torsional radius of gyration           | 0.3411  |
| R <sub>o</sub> (in)               | Polar radius of gyration               | 2.2935  |
| Beta                              | Torsional Flexural Constant            | 0.9487  |



### CODES AND STANDARDS:

**EB Metal US/Super Stud** products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006 – 2024
- AISI S100-16 (2020) w/S2-20 and AISI S220-20
- Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized coating: ASTM A653/A653M or equivalent
- UL Designs: U411, U412, U419, U420, U425, U435, U451, U465, UL 263, CIKV.R38201, CIKV7.R38201
- Tested in accordance with ASTM E119; ANSI/UL 263
- Members and tolerances: ASTM C645; AISI S220, AISI S201, AISI S202
- Meets ASTM C754 when installed properly in structure.

**For LEED Letter requests please submit through:** ebmetal.us. or buysuperstud.com

**NEW HAMPSHIRE FACILITY**  
12 TALLWOOD DRIVE  
BOW, NH 03304  
P: 601-584-7550

**MISSISSIPPI FACILITY**  
53 W L RUNNELS IND DR  
HATTIESBURG, MS 39401  
P: 601-584-7550

**NEW JERSEY FACILITY**  
2960 WOODBRIDGE AVE  
EDISON, NJ 08837  
P: 732-662-6200