



800-477-7883
buysuperstud.com

Super Stud Building Products

Technical Services: technical@buysuperstud.com

New Jersey
2960 Woodbridge Avenue Edison, NJ 08837
732-662-6200

Mississippi
53 W L Runnels Industrial Dr Hattiesburg, MS 39401
601-584-7550

SUPERMAXX STUD

Specification Section: 05.40.00 (Cold-Formed Metal Framing)

800SMX200-97 (50ksi) Standard Punch

97mils (12ga) Coating: CP60 (G60) Standard or CP90 (G90) Available

Geometric Properties

Web Depth	8 in	Yield Strength, F_y	50 ksi
Flange Width	2 in	Ultimate, F_u	65 ksi
Design Thickness	0.1017 in	Min. Steel Thickness	0.0966 in
First Lip:	1.125 in	Second Lip:	0.5 in

Gross Section Properties

Cross Sectional Area (A)	1.4356 in ²
Product Weight per Linear Foot	4.8810 lb/ft
Moment of Inertia (I_x)	12.7478 in ⁴
Section Modulus (S_x)	3.1870 in ³
Radius of Gyration (r_x)	2.9799 in
Weak Axis Moment of Inertia (I_y)	0.8417 in ⁴
Weak Axis Radius of Gyration (r_y)	0.7657 in
Depth-to-Thickness Ratio (h/t)	74

Effective Section Properties, Strong Axis

Effective Area (A_e)	0.9515 in ²
Moment of Inertia for Deflection (I_{xe})	12.7192 in ⁴
Section Modulus (S_{xe})	3.1798 in ³
Allowable Bending Moment (M_a)	109.7000 in-k
Allowable Shear Force in Web (at Punchout) (V_y)	5,940 lb

Torsional Properties

St. Venant Torsion Constant ($J \times 1000$)	4.9495 in ⁴
Warping Constant (C_w)	13.1214 in ⁶
Distance from Shear Center to Neutral Axis (X_o)	1.6102 in
Radius of Gyration (r_o)	3.4726 in
Torsional Flexural Constant (Beta)	0.7850

Codes and Standards

Super Stud products comply with the applicable provisions of the following:

International Building Code (IBC): 2006 – 2024

Complies with AISI S100-16 (2020) w/S2-20. Effective properties incorporate the strength increase from the cold work of forming

Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M


Galvanized coating: ASTM A653/A653M

Members and tolerances: ASTM C955; AISI S240, AISI S201, AISI S202

Meets ASTM C1007 when installed properly in structure.

3rd party Certification

SuperMAXX Joists have flanges with double returns for superior strength and stiffness that dramatically increase spans and capacities.




Two hole pattern options Standard Structural Punch

First oval punchout is centered 12" from beginning of member; subsequent punchouts are 24" on center (o.c.). Center of last punchout is no less than 12" from end of member.

Maxx Punch

Only available in 6" and 8" studs. First oval punchout is centered at 12" from beginning of member. Three reinforced circular holes 6" o.c. follow and pattern repeats. Oval punchouts are at 24" o.c. Center of last punch out is no less than 12" from end of member.



Sustainability

For LEED letters contact Technical Services at technical@buysuperstud.com or visit

<https://www.buysuperstud.com/specs-resources/sustainability-and-green-building>



SMX © 2025 Super Stud Building Products