

362S162-54 (50ksi) (Standard Punch)

Product Description: 3-5/8" Stud 16GA (1-5/8" Flange, 54 mil)

Coating: G60 (standard), G90 (special order)



Specification Section: 05.40.00 (Cold-Formed Metal Framing)

GEOMETRIC PROPERTIES			
Web Depth	3.625 in.	Yield Strength, F_y	50 ksi
Flange Width	1.625 in.	Design Thickness	0.0566 in.
Lip Length	0.500 in.	Min. Design Thickness	0.0538 in.

GROSS PROPERTIES		
Area (in ²)	Total cross-sectional steel area	0.422
Weight (lb/ft)	Linear weight per foot	1.44
I_x (in ⁴)	Moment of inertia about the x-axis	0.873
S_x (in ³)	Section modulus about the x-axis	0.482
R_x (in)	Radius of gyration about the x-axis	1.438
I_y (in ⁴)	Moment of inertia about the y-axis	0.154
R_y (in)	Radius of gyration about the y-axis	0.605

EFFECTIVE PROPERTIES		
I_x (in ³)	Effective moment of inertia (x-axis)	0.873
S_x (in ³)	Effective section modulus (x-axis)	0.454
M_a (in-k)	Allowable bending moment-effective section modulus	13.60
M_{ad} (in-k)	Allowable bending moment-distortional buckling	12.87
V_a (lb)	Allowable shear force in web	3372
$V_{a_{net}}$ (lb)	Allowable strong axis shear at punchout	1016

TORSIONAL PROPERTIES		
$J \times 1000$ (in ⁴)	St. Venant torsional constant	0.451
C_w (in ⁶)	Warping constant	0.457
X_o (in)	Distance from shear center to centroid	-1.283
m (in)	Distance from shear center to mid-plane of web	0.774
R_o (in)	Polar radius of gyration	2.020
Beta	Torsional Flexural Constant	0.597



First punchout is centered 12" from beginning of member;
subsequent punchouts are 24" on center (o.c.). Center of last
punchout is no less than 12" from end of member.

CODES AND STANDARDS:

Super Stud products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006–2024
- AISI S100-16 (2020) w/S2-20 (effective properties include cold-work strength increase)
- Sheet Steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized Coating: ASTM A653/A653M

Structural Members:

- ASTM C955; AISI S240
- Installed per ASTM C1007

Additional Standards:

- AISI S201; AISI S202

3rd Party Certification

For LEED Letter requests please submit through: www.buysuperstud.com