

Product Submittal Sheet

New Jersey Facility

2960 Woodbridge Avenue Edison, NJ 08837-3406 P: 732-662-6200

technical@buysuperstud.com

Mississippi Facility

53 W. L. Runnels Industrial Drive Hattiesburg, MS 39401-8320 P: 601-584-7550

sales@superstudsouth.com

Specification Section: 05.40.00 (Cold-Formed Metal Framing)

Product Category: Deflection Clips

Product Name: SS-HW600-12 and SS-HW 600-14 Head-Of-Wall

Coating: CP90 (G90) Available

Material: ASTM A1003 and A653 ST50H

800-477-7883

buysuperstud.com

Properties

Vertical Movement 3 in
Width: 5.5 in
Height: Vertical (Slotted) Leg 4.75 in
Depth: Horizontal (top) leg 5.5 in
Yield Strength 50 ksi
Tensile Strength 65 ksi

SS-HW600-12

Design Thickness: 0.1017" Minimum Thickness: 0.0966" Mil Thickness: 97 • Gauge: 12



SS-HW600-14

Design Thickness: 0.0713" Minimum Thickness: 0.0677" Mil Thickness: 68 • Gauge: 14

Capacities for (3) #12 screws SS-HW600-12 head-of-wall Clip		
33 mil 33 KSI	300	
43 mil 33 KSI	380	
54 mil 50 KSI	725	
68 mil 50 KSI	915	
97 mil 50 KSI	1170	
118 mil 50 KSI	1170	

SS-HW600-14 head-of-wall Clip	
33 mil 33 KSI	300
43 mil 33 KSI	380
54 mil 50 KSI	508
68 mil 50 KSI	641

97 mil 50 KSI

118 mil 50 KSI

Preliminary clip capacities for SS-HW600 clip

For SS-HW350, use 2/3 these values: based on (2) #12 screws.

Note that capacities for 43 and 54 mil clips have been interpolated from test data on 33 and 68 mil samples. These values have been reduced based on AISI S100-12 chapter F safety factors. Field values will likely be higher. Super Stud is in the process of developing 3rd party verified and tested values.

Codes and Standards

Super Stud products comply with the applicable provisions of the following:

International Building Code (IBC): 2006 – 2021

Sheet steel: ASTM A1003/A1003M; ASTM A653/A653M

Galvanized coating: ASTM A653/A653M

Members and tolerances: ASTM C955; AISI S240, AISI S201, AISI S202

Meets ASTM C1007 when installed properly in structure.





820

820