

350T200-43 Track


Product Description: 3-1/2" Track 18GA (2" Leg, 43mil)

Coating: G60 (standard), G90 (special order)

Specification Section: 05.40.00 (Cold-Formed Metal Framing)

GEOMETRIC PROPERTIES			
Web Depth	3.5 in.	Yield Strength, F_y	33 ksi
Leg Width	2 in.	Design Thickness	0.0451 in.
		Min. Steel Thickness	0.0428 in.

GROSS PROPERTIES		
Area (in ²)	Total cross-sectional steel area	0.338
Weight (lb/ft)	Linear weight per foot	1.15
I_x (in ⁴)	Moment of inertia about the x-axis	0.749
S_x (in ³)	Section modulus about the x-axis	0.409
R_x (in)	Radius of gyration about the x-axis	1.489
I_y (in ⁴)	Moment of inertia about the y-axis	0.140
R_y (in)	Radius of gyration about the y-axis	0.645
EFFECTIVE PROPERTIES		
I_x (in ³)	Effective moment of inertia (x-axis)	0.601
S_x (in ³)	Effective section modulus (x-axis)	0.258
M_a (in-k)	Allowable bending moment-effective section modulus	5.10
V_a (lb)	Allowable shear force in web	1740
TORSIONAL PROPERTIES		
$J \times 1000$ (in ⁴)	St. Venant torsional constant	0.2291
C_w (in ⁶)	Warping constant	0.323
X_o (in)	Distance from shear center to centroid	-1.280
m (in)	Distance from shear center to mid-plane of web	0.758
R_o (in)	Polar radius of gyration	2.067
Beta	Torsional Flexural Constant	0.616



CODES AND STANDARDS:

Super Stud/EB Metal US products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006–2024
- AISI S100-16 (2020) w/S2-20
- Sheet Steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized Coating: ASTM A653/A653M

Structural Members:

- ASTM C955; AISI S240
- Installed per ASTM C1007

Additional Standards:

- AISI S201; AISI S202

3rd Party Certification

For LEED Letter requests please submit through:
www.buysuperstud.com or www.ebmetal.us