

600T300-33 Track

Product Description: 6" Track STR 20GA (3" Leg, 33mil)


Coating: G60 (standard), G90 (special order)

Specification Section: 05.40.00 (Cold-Formed Metal Framing)

GEOMETRIC PROPERTIES			
Web Depth	6 in.	Yield Strength, Fy	33 ksi
Leg Width	3 in.	Design Thickness	0.0346 in.
		Min. Steel Thickness	0.0329 in.

**When web height-to thickness ratio exceeds 260, or flange width-to-thickness ratio exceeds 60, effective properties are not calculated (limitations in AISI Section B4.1).*

GROSS PROPERTIES		
Area (in ²)	Total cross-sectional steel area	0.415
Weight (lb/ft)	Linear weight per foot	1.41
I _x (in ⁴)	Moment of inertia about the x-axis	2.559
S _x (in ³)	Section modulus about the x-axis	0.833
R _x (in)	Radius of gyration about the x-axis	2.484
I _y (in ⁴)	Moment of inertia about the y-axis	0.384
R _y (in)	Radius of gyration about the y-axis	0.962
EFFECTIVE PROPERTIES		
I _x (in ³)	Effective moment of inertia (x-axis)	-
S _x (in ³)	Effective section modulus (x-axis)	-
M _a (in-k)	Allowable bending moment-effective section modulus	-
V _{a_g} (lb)	Allowable shear force in web	-
TORSIONAL PROPERTIES		
J x 1000 (in ⁴)	St. Venant torsional constant	0.166
C _w (in ⁶)	Warping constant	2.520
X _o (in)	Distance from shear center to centroid	-1.853
m (in)	Distance from shear center to mid-plane of web	1.112
R _o (in)	Polar radius of gyration	3.244
Beta	Torsional Flexural Constant	0.755



CODES AND STANDARDS:

Super Stud/EB Metal US products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006–2024
- AISI S100-16 (2020) w/S2-20
- Sheet Steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized Coating: ASTM A653/A653M

Structural Members:

- ASTM C955; AISI S240
- Installed per ASTM C1007

Additional Standards:

- AISI S201; AISI S202

3rd Party Certification

For LEED Letter requests please submit through:
www.buysuperstud.com or www.ebmetal.us