

362S300-68 (Standard Punch)

Product Description: 3-5/8" Stud 14GA (3" Flange, 68 mil)

Coating: G60 (standard), G90 (special order)



Specification Section: 05.40.00 (Cold-Formed Metal Framing)

GEOMETRIC PROPERTIES			
Web Depth	3.625 in.	Yield Strength, F_y	50 ksi
Flange Width	3 in.	Design Thickness	0.0713 in.
Lip Length	0.625 in.	Min. Steel Thickness	0.0677 in.

GROSS PROPERTIES		
Area (in ²)	Total cross-sectional steel area	0.738
Weight (lb/ft)	Linear weight per foot	2.51
I_x (in ⁴)	Moment of inertia about the x-axis	1.716
S_x (in ³)	Section modulus about the x-axis	0.947
R_x (in)	Radius of gyration about the x-axis	1.525
I_y (in ⁴)	Moment of inertia about the y-axis	0.900
R_y (in)	Radius of gyration about the y-axis	1.105

EFFECTIVE PROPERTIES		
I_x (in ³)	Effective moment of inertia (x-axis)	1.685
S_x (in ³)	Effective section modulus (x-axis)	0.726
M_a (in-k)	Allowable bending moment-effective section modulus	21.74
M_{ad} (in-k)	Allowable bending moment-distortional buckling	22.59
V_a (lb)	Allowable shear force in web	4370
$V_{a_{net}}$ (lb)	Allowable strong axis shear at punchout	1004

TORSIONAL PROPERTIES		
$J \times 1000$ (in ⁴)	St. Venant torsional constant	1.250
C_w (in ⁶)	Warping constant	2.833
X_o (in)	Distance from shear center to centroid	-2.640
m (in)	Distance from shear center to mid-plane of web	1.512
R_o (in)	Polar radius of gyration	3.243
Beta	Torsional Flexural Constant	0.337



First punchout is centered 12" from beginning of member; subsequent punchouts are 24" on center (o.c.). Center of last punchout is no less than 12" from end of member.

CODES AND STANDARDS:

Super Stud products comply with the applicable provisions of the following:

- International Building Code (IBC): 2006–2024
- AISI S100-16 (2020) w/S2-20 (effective properties include cold-work strength increase)
- Sheet Steel: ASTM A1003/A1003M; ASTM A653/A653M
- Galvanized Coating: ASTM A653/A653M

Structural Members:

- ASTM C955; AISI S240
- Installed per ASTM C1007

Additional Standards:

- AISI S201; AISI S202

3rd Party Certification

For LEED Letter requests please submit through: www.buysuperstud.com